

### DATA SHEET OF INSULATING CASTABLE

SL NO	PARAMETERS	SPECIFICATION
1	PRODUCT BRAND	IND INCAST 9
2	DESCRIPTION	MEDIUM DENSITY INSULATING CASTABLE
3	MAX SERVICE TEMP, °C	1200
4	NATURE OF BOND	HYDRAULIC
5	MAX GRAIN SIZE, MM	6
6	INSTALLATION	TAMPING
7	CHEMICAL ANALYSIS	
	Al <sub>2</sub> O <sub>3</sub> , %	25.00 MIN
	Fe <sub>2</sub> O <sub>3</sub> , %	6.00 MAX
	CaO, %	12.00 MAX
8	WATER REQD FOR CASTING, %	40 to 50
9	BD, g/cc	
	After drying at 110°C / 24 hours	1.05 MAX
10	CCS, kg/cm <sup>2</sup>	
	After drying at 110°C / 24 hours	15 MIN
	After heating at 1200°C / 3 hours	10 MIN
11	PERMANENT LINEAR CHANGE, %	
	After heating at 1200°C / 3 hours	± 1.00 MAX
12	THERMAL CONDUCTIVITY, kcal/m/hr/°C	
	At 500°C HF	0.28 MAX
13	REFRACTORINESS, Orton / °C	13 / 1349 MIN
14	PACKAGING, Bags	50 KG
15	SHELF LIFE, Months	9



16	DELIVERY STATE	DRY
----	----------------	-----